

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

ABSTRACT**COEXTRUSION TIE FOR POLYESTER BASED ON COGRAFTED
METALLOCENE POLYETHYLENE AND LLDPE AND ON METALLOCENE
POLYETHYLENE**

A subject matter of the invention is a coextrusion tie, which comprises:

- 5 to 35% by weight of a polymer (A) itself composed of a blend of 80 to 20% by weight of a metallocene polyethylene (A1) with a density of between 0.863 and 0.915 and of 20 to 80% by weight of a non-metallocene LLDPE polyethylene (A2) with a density of between 0.900 and 0.950, the blend of polymers (A1) and (A2) being cografterd;

- 95 to 65% by weight of metallocene polyethylene (B) homo- or copolymer, the comonomer of which comprises 3 to 20 carbon atoms, preferably 4 to 8 carbon atoms, the density of which is between 0.863 and 0.915 and the MFI of which is between 0.5 and 30, preferably between 3 and 15, g/10 min; the total forming 100%, the blend of (A) and (B) being such that its MFI is between 0.1 and 15, preferably between 1 and 13, g/10 min.